United States Mint, Philadelphia, Penn.,

MELTER AND REFINER'S DEPARTMENT,

13th May, 1879.

Sir,

Herewith enclosed please find the Reports on Gold & Silver Melting for the Month of April, 1879.

The average wastage in daily melting Gold and Silver has been $\frac{47}{1000}$ and $\frac{85}{1000}$ respectively; or about one half the legal allowance, to be reduced by assay slips, and sweep.

The number of melts condemned has been but two (2), about one-third of one per cent.

Respectfully yours
J. A. C. Booth.
M & R

Hon. A. Loudon Snowden
Superintendent.

RG104 E-1 Box 116

NARA RG104, Entry 1, Box 116

United States Mint, Philadelphia, Penn.,
Melter and Refiner's Department,
May 13, 1879

Sir,

Herewith enclosed please find the Reports on Gold & Silver Melting for the Month of April, 1879.

The average wastage in daily melting Gold and Silver has been 47/1000 and 85/1000 respectively, or about one half the legal allowance, to be reduced by assay slips, and sweep.

The number of melts condemned has been but two (2), about one-third of one per cent.

Respectfully yours,
Jas. C. Booth
M & R

Hon. A. Loudon Snowden
Superintendent.